SCANFI Aps

ENERGIVEJ 2 . DK-9300 SAEBY . TLF. +45 98 46 27 11 . FAX +45 98 46 18 15



Alfa compact abrasion



Its type of braid and extrusion treatment works together for a great abrasion resistance when bottom trawling. It can resist abrasion 60% longer than any other twine. It has a good breaking strength of 6,5 grams per denier, which is around 30% more than standard polyethylene.

Diameter	Mts/kg	Breaking strength
1,8 mm	610	76
2,5 mm	328	123
3,0 mm	248	165
4,0 mm	148	255
5,0 mm	98	355
6,0 mm	61	603

Braided nylon



Scanfi supply braided nylon netting. The twines are made with the best raw materials from various parts of the world.

D	iameter	Mts/kg	Breaking strength
	1,3 mm	600	90
	1,8 mm	400	180
	2,0 mm	270	250
	3,0 mm	180	335
	4,0 mm	130	410
	4,5 mm	105	510
	6,0 mm	75	580
	7,0 mm	60	740
	8,0 mm	50	820